



PAN CARBON FABRIC SPECIFICATION SHEET

PCW

Fabric	Weave	Weight (g/m ²)	Width (cm)	No. of threads/cm		Tex of filament		Thickness (mm)
				Warp	Weft	Warp	Weft	
PCW-95-P-1	Plain	95	120	7	7	70	70	0.15
PCW-122-P-1	Plain	122	100	--	--	70	70	0.15
PCW-160-P-3	Plain	160	120	4	4	200	200	0.25
PCW-200-P-3	Plain	200	120	5	5	200	200	0.30
PCW-200-T-3	2x2 Twill	200	120	5	5	200	200	0.30
PCW-240-P-3	Plain	240	120	6	6	200	200	0.35
PCW-240-T-3	2x2 Twill	240	120	6	6	200	200	0.35
PCW-280-T-3	4x4 Twill	280	120	7	7	200	200	0.40
PCW-300-T-3	1x3 Twill	300	100	12	3	200	200	0.45
PCW-300-P-6	Plain	300	120	3.7	3.7	400	400	0.50
PCW-400-T-6	2x2 Twill	400	120	5	5	400	400	0.60
PCW-300-P-12	Plain	300	120	3	3	800	200	0.50
PCW-420-T-12	2x2 Twill	420	120	2.6	2.6	800	800	0.65
PCW-480-P-12	Plain	480	120	3	3	800	800	0.80
PCW-650-T-12	2x2 Twill	650	120	4	4	800	800	0.90